

pbs
europan TEXTURA

EUROPAN TEXTURA is a pre-finished compressed fibre cement sheet with a unique textured surface used for external cladding, balcony panels, soffits, weatherboards and louvres. EUROPAN TEXTURA can be produced in an almost unlimited range of colours.

Product Information

1. Product composition

EUROPAN TEXTURA sheets consist of the following:

- Portland cement
- Mineral fillers
- Organic reinforcing fibres
- Additives
- Water-based acrylate dispersion with granular structure on the face
- Vinylidene chloride copolymer (PVDC) with a paraffin wax on the reverse side

2. Production method

EUROPAN TEXTURA sheets are manufactured on a Hatschek machine and are in an additional step compressed and air cured. EUROPAN TEXTURA is then finished with a water-based acrylate finish with granular structure on the face and vinylidene chloride copolymer (PVDC) with a paraffin wax on the reverse side.

EUROPAN TEXTURA is not required to **and cannot** be repainted. Consult PBS Distributors before applying other coatings on the product.

3. Dimensions and tolerances

Standard thickness: 8 mm (12mm thick panels can be manufactured on indent basis).

Untrimmed	Trimmed
1280 x 2530 mm	1250 x 2500 mm
1280 x 3130 mm	1250 x 3100 mm

Tolerances

	Untrimmed	After cutting
Thickness	+/- 0.5 mm	+/- 0.5 mm
Length and width	+/- 5.0 mm	+/- 1.5 mm
Squareness	2.0 mm / m	1.0 mm / m

4. Weight

Thickness	Weight
5 mm	9.5 kg/m ²
8 mm	15.4 kg/m ²
12 mm	22.8 kg/m ²

TE-PR-TE-PI-110406

©PBS Distributors

5. Colours

EUROPAN TEXTURA has a textured granular surface.

An overview of the colours with respective product codes is given in the following tables.

There are 15 colour options available

Name	Code
Black 001	TA 001
White 102	TG 102
Grey 205	TG 205
Grey 206	TG 206
Grey 207	TA 207
Red 304	TA 304
Red 305	TA 305
<i>Blue 403*</i>	<i>TG 403</i>
<i>Blue 404*</i>	<i>TG 404</i>
<i>Blue 405*</i>	<i>TA 405</i>
<i>Green 504*</i>	<i>TG 504</i>
<i>Yellow 601*</i>	<i>TG 601</i>
Yellow 602	TG 602
Orange 701	TA 701
<i>Beige 803*</i>	<i>TG 803</i>

* Minimum quantities apply.

Consult with PBS Distributors for minimum quantities and lead times.

Other colours are available on request in minimum quantities.

6. Technical properties (average values)

Density		: 1650 kg/m ³
Bending strength (24h immersed in water)	//	: 24.0 N/mm ²
	T	: 17.0 N/mm ²
Modulus of elasticity		: 15000 N/mm ²
Maximum water absorption after 24 hours		: < 1 %
Thermal expansion coefficient		: 10 x 10 ⁻⁶ m/mK
Thermal conductivity coefficient		: 0.6 W/mK
Frost resistance		: frost resistant
Reaction to fire according to EN13501-1		: A2
Heat and smoke release rates AS/NZS 3837		: Natura base sheet for EUROPAN PICTURA has performance level A
EUROPAN PICTURA meets the requirements of the European Norm EN 12467 and is CE-marked.		

7. Advantages

- Good fire behaviour
- Resistant to high temperatures
- Water resistant
- Resistant to fungus, bacteria, insects, vermin, etc.
- Resistant to many chemicals
- Environmentally friendly, no harmful gas emissions
- Frost resistant

TE-PR-TE-PI-110406

©PBS Distributors

- High dimensional stability
- Strong and rigid sheet
- High UV resistance
- Strong, resistant surface
- Larger dimensions available
- Wide range of colours

8. Working guidelines

Cutting:

- PBS Distributors operates a CNC waterjet cutting machine in Auckland that facilitates the cutting of intricate designs with minute tolerances. Please contact PBS Distributors for more information.

For on site cutting:

- On a **stationary saw**, slow rotation with tungsten carbide-tipped blade or fast rotation with a fluted diamond cutting blade.
- With a **hand circular saw** (with rail), slow rotation with tungsten carbide-tipped blade or fast rotation with a fluted diamond cutting blade.
- With a **jigsaw** with tungsten carbide-tipped tooth cutting blade

All power tools must be used over a guide. Tools must never be dragged across the surface of the sheets.

Edge finish:

- Use a fine emery cloth or sanding block

Drilling:

- For holes: carbide tipped twist drill with a 60° nose angle
- For round apertures: cup drill or circular cutter, carbide-tipped

The sheet should be supported around the hole to be drilled (e.g. by a wooden surface).

- Cutting and drilling must take place in a dry environment. All residual dust must be removed immediately from the sheet with a dry towel to avoid permanent stains.

Fixing:

The method and choice of the fixings (e.g. stainless steel, aluminium ...) is dependent on the application and the environment.

1) Structural adhesive (concealed fixing):

EUROPAN TEXTURA can be fixed with a structural adhesive. The back of the sheet must be sanded (sand paper P80) and sealed at the area where the adhesive is applied. The only adhesive to be used is specified by PBS Distributors in accordance with the PBS Distributors application guidelines. Further information is available from PBS Distributors.

2) Screwing:

Use screws as specified by PBS Distributors. On 40 mm thick timber battens use 60 x 10 swg stainless steel screws with a square drive and stainless steel cup washers. EUROPAN TEXTURA cannot be fixed with countersunk screws.

Sheets need to be predrilled with the appropriate diameter for fixed and sliding points.

Follow the fixing patterns as specified by PBS Distributors. Min distance to the edge of the sheet is 25 mm and 100 and 50 mm to the edges at the corner of the sheets.

3) Riveting:

Aluminium or stainless steel rivets and cylinders in accordance with the PBS Distributors specifications are only possible on aluminium profiles with sufficient flange width. Please contact PBS Distributors for more information.

Sheets need to be predrilled with the appropriate diameter for fixed and sliding points. Follow the fixing patterns as specified by PBS Distributors. Min distance to the edge of the sheet is 25 mm and 150 and 50 mm to the edges at the corner of the sheets.

Caulking:

Only use products recommended by PBS Distributors. Non-neutral silicones or thiokols can result in staining.

Health and safety aspects:

While the sheets are being processed, dust will be released which may irritate airways and eyes. It is recommended that a minimum P2 dust mask and safety goggles be worn. Appropriate dust extraction or proper ventilation should be used depending on the room in which the work is being carried out or the equipment being used. Long-term exposure to dust may be harmful to health.

9. Maintenance and cleaning

For minor soiling, wash with a mild household detergent or soft soap solution followed by rinsing with clear water. EUROPAN TEXTURA is recommended to be chemical cleaned according to PBS Distributors cleaning advice. No abrasive products or tools shall be used to clean the surface. Please refer to the PBS cleaning advice for more specific cleaning advice.

Important remark: EUROPAN TEXTURA is pre-finished. Attempts to apply additional coatings on the product, will not be the responsibility of PBS Distributors.

10. Handling

The sheets are packed on pallets. They must be kept dry during transport. The sheets must be horizontally stacked on a flat surface. The sheets must always be sufficiently supported so that they do not sag. The sheets must be stored in a dry ventilated space. If the sheets are stored outside, they must always be protected against rain by a tarpaulin or plastic sheet. If the sheets do become wet in the packing, all packaging must be removed and the sheets must be wiped dry and separated to dry completely. A sheet must always be lifted from a stack by two people and then be carried on edge.

11. Guarantee

The guarantee and the guarantee conditions are available on request from PBS Distributors.